

## FUGRO TECHNICAL SERVICES LIMITED

MateriaLab Division,  
Fugro Development Centre,  
5 Lok Yi Street, 17 M.S. Castle Peak Road,  
Tai Lam, Tuen Mun, N.T., Hong Kong.

Tel : +852-2450 8233  
Fax : +852-2450 6138  
E-mail : matlab@fugro.com.hk  
Website : www.materialab.com.hk

# **MateriaLab**

### **REPORT ON THE SURFACE SPREAD OF FLAME TEST TO BS 476 : PART 7 : 1997 ON "MAGICSTONE" MODEL CM201 GLACIER WHITE COLOUR SOLID SURFACE COMPOSITE ACRYLIC**

Client : Guangzhou Relang Industrial Co., Ltd.  
Project : Fire Testing on "Magicstone" Material  
Client Ref. : --  
Report No. : 091232ST90233(1)  
Date : 05 June 2009



## FUGRO TECHNICAL SERVICES LIMITED

MaterialLab Division,  
Fugro Development Centre,  
5 Lok Yi Street, 17 M.S. Castle Peak Road,  
Tai Lam, Tuen Mun, N.T., Hong Kong.

Tel : +852-2450 8233  
Fax : +852-2450 6138  
E-mail : matlab@fugro.com.hk  
Website : www.materiallab.com.hk

# MaterialLab

## CONTENT

- |     |                        |
|-----|------------------------|
| 1.0 | Introduction           |
| 2.0 | Description of Samples |
| 3.0 | Purpose of Test        |
| 4.0 | Test Procedure         |
| 5.0 | Date of Test           |
| 6.0 | Results of Test        |
| 7.0 | Conclusion             |





## FUGRO TECHNICAL SERVICES LIMITED

MateriaLab Division,  
Fugro Development Centre,  
5 Lok Yi Street, 17 M.S. Castle Peak Road,  
Tai Lam, Tuen Mun, N.T., Hong Kong.

Tel : +852-2450 8233  
Fax : +852-2450 6138  
E-mail : matlab@fugro.com.hk  
Website : www.materialab.com.hk

# MateriaLab

Client Ref. : --

Page 1 of 4

Report No. : 091232ST90233(1)

### 1.0 Introduction

Fugro Technical Services Limited, MateriaLab Division was commissioned by the client, Guangzhou Relang Industrial Co., Ltd. to arrange a Surface Spread of Flame Test in accordance with BS 476 : Part 7 : 1997 on samples of "Magicstone" Model CM201, Glacier White Colour Solid Surface Composite Acrylic Material.

The test was conducted by Fugro Technical Services, MateriaLab Division's approved sub-contract Laboratory, TÜV SÜB PSB Pte. Ltd. TÜV SÜB PSB Pte. Ltd. is a Singapore Laboratory accredited by SAC-SINGLAS, with accreditation number LA-007-0380-A, LA-2007-0380-A-1, LA-2007-0381-F, LA-2007-0382-B, LA-2007-0383-G, LA-2007-0384-G, LA-2007-0385-E and LA-2007-0386-C.

Six samples were prepared by the client and received by Fugro Technical Services Limited, MateriaLab Division on 20 April 2009. The samples were given Lab. I.D. : ST90233/7-12.

### 2.0 Description of Samples

Nine pieces of specimen, said to be "Magicstone" (12.3 mm thick x 1750 kg/m<sup>3</sup>) model CM201, Glacier White colour Solid Surface Composite acrylic material comprising of MMA, Polyester, ATH and Hardener, each of nominal size of 885 mm x 270 mm were submitted.

### 3.0 Purpose of Test

To determine the tendency of the surface of a material or a combination of materials to support the spread of flame across its surface and to classify the surface according to the test given in British Standard 476 : Part 7 : 1997.





Client Ref. : --

Page 2 of 4

Report No. : 091232ST90233(1)

#### 4.0 Test Procedure

Prior to test, the specimens were prepared and conditioned in accordance with paragraphs 5.3 to 5.6 of the standard and secured to a specimen holder as described in paragraph 6.3.

Six specimens, backed with calcium silicate board, were tested with the polished face exposed to the specified thermal radiation from the apparatus described in paragraph 6.1 of the standard. The intensity of the radiated heat incident on the specimen varies with distance from the hotter end, so that when the specified calibration panel is mounted in the place to be occupied by the specimen, the irradiance of the radiometer is as given in Table 1. The test was terminated when the flame front reached the 825 mm reference line, or after 10 minutes has elapsed, whichever is the shorter.

Table 1 : Irradiance Along Horizontal Reference Line on the Calibration Board

Distance along reference line from inside edge of specimen holder (mm)	Irradiance (kW/m <sup>2</sup> )		
	specified	min.	max.
75	32.5	32.0	33.0
225	21.0	20.5	21.5
375	14.5	14.0	15.0
525	10.0	9.5	10.5
675	7.0	6.5	7.5
825	5.0	4.5	5.5





**FUGRO TECHNICAL SERVICES LIMITED**

MaterialLab Division,  
Fugro Development Centre,  
5 Lok Yi Street, 17 M.S. Castle Peak Road,  
Tai Lam, Tuen Mun, N.T., Hong Kong.

Tel : +852-2450 8233  
Fax : +852-2450 6138  
E-mail : matlab@fugro.com.hk  
Website : www.materialab.com.hk

**MaterialLab**

Client Ref. : --  
Report No. : 091232ST90233(1)

Page 3 of 4

**5.0 Date of Test**

07 May 2009

**6.0 Results of Test**

Specimen No.	1	2	3	4	5	6
Spread of flame at first 1½ minutes (mm)	0	0	0	0	0	0
Distance (mm)	Time of spread of flame to indicated distance (minutes • seconds)					
Start of flaming	8.35	Nil	Nil	9.24	Nil	Nil
75	8.37	--	--	9.27	--	--
165	--	--	--	--	--	--
190					--	--
215						
240						
265						
290						
375						
455						
500						
525						
600						
675						
710						
750						
785						
825						
865						
Time of maximum spread of flame (minutes • seconds)	8.39	--	--	9.29	--	--
Distance of maximum spread of flame (mm)	75-165	0	0	75-165	0	0
Comments	None					





**FUGRO TECHNICAL SERVICES LIMITED**

MaterialLab Division,  
Fugro Development Centre,  
5 Lok Yi Street, 17 M.S. Castle Peak Road,  
Tai Lam, Tuen Mun, N.T., Hong Kong.

Tel : +852-2450 8233  
Fax : +852-2450 6138  
E-mail : matlab@fugro.com.hk  
Website : www.materiallab.com.hk

**MaterialLab**

Client Ref. : --  
Report No. : 091232ST90233(1)

Page 4 of 4

**7.0 Conclusion**

In accordance with the class definitions specified in the Standard, the test results show that the sample tested has a Class One Surface Spread of Flame.

Classification of Surface Spread of Flame

Classification	Spread of flame at 1.5 min.		Final spread of flame	
	Limit (mm)	Limit for one specimen in sample (mm)	Limit (mm)	Limit for one specimen in sample (mm)
Class 1	165	165 + 25	165	165 + 25
Class 2	215	215 + 25	455	455 + 45
Class 3	265	265 + 25	710	710 + 75
Class 4	Exceeding the limits for class 3			

Remarks : 1.) The test results relate only to the behaviour of the test specimens of the product under the particular conditions of test ; they are not intended to be the sole criterion for assessing the potential fire hazard of the product in use.



Checked by :                     

Certified by :                       
Chan Chun Wai Ivan  
Manager (Product Testing Laboratory)

Date :                     

Date :